

15 mil Clear

MECHANICAL PROPERTIES

Thickness	15 mil
Tensile Strength at Break	28,500 PSI
Break Strength	420 lb/inch
Elongation at Break	140 %
Peel Strength	8 lb/inch

OPTICAL & SOLAR PROPERTIES

	3mm Single
Visible Light Transmitted	87%
Visible Light Reflected (Int)	11%
Visible Light Reflected (Ext)	11%
Ultra Violet Block	99%
Total Solar Energy Reflected	11%
Total Solar Energy Transmitted	77%
Total Solar Energy Absorbed	12%
Glare Reduction	3%
Shading Coefficient	0.94
Solar Heat Gain Coeff. (G-Value)	0.82
U-Value Winter (IP)	1.07
U-Value Winter (SI)	6.07
Total Solar Energy Rejected	18%

R39803T PS

SAFETY ACCREDITATIONS

Impact	EN 356 P4A	✓ 15 mil x 2
--------	------------	--------------

ED-B DS No 1232, March 2012

safety & security

